



189 W. Clarkston Rd. B203, Lake Orion, Michigan 48362 USA  
(Toll Free) 1-877-777-4514 (Intl) 248-845-4515 (Fax) 248-287-4515  
www.PremierPlasticResins.com info@premierplasticresins.com

---

## Typical Data Sheet

---

### PPR-HDPE01

#### High Density Polyethylene 20 Melt .955 Density Natural

Test Description	Method	Properties	
		English	S.I.
Tensile Strength at Yield, psi (Mpa)	D-638	3,100	21.4
Elongation at Break, %	D-638	200	
Flexural Modulus (Tangent), psi (Mpa)	D-790	120,000	828
Melt Flow Rate, g/10 min. 190/2160	D-1238	20.0	
Specific Gravity	D-792	0.955	
Heat Deflection Temperature			
At 264 psi, F (C)	D-648	130	54
At 66 psi, F (C)	D-648	155	68
Linear Mold Shrinkage	D-955	0.0200	

---

Values shown are averages and not to be construed as specifications.