



189 W. Clarkston Rd. B203, Lake Orion, Michigan 48362 USA
(Toll Free) 1-877-777-4514 (Intl) 248-845-4515 (Fax) 248-287-4515
www.PremierPlasticResins.com info@premierplasticresins.com

Typical Data Sheet

PPR-PPCO08

Polypropylene Copolymer 30 Melt 2 Izod Black

| Test Description | Method | Properties | |
|--|--------|------------|-------|
| | | English | S.I. |
| Tensile Strength at Yield, psi (Mpa) | D-638 | 3,550 | 24.5 |
| Elongation at Yield, % | D-638 | 12 | |
| Flexural Modulus (Tangent), psi (Mpa) | D-790 | 160,000 | 1,100 |
| Izod Impact (Notched), ft-lb./in (J/m) | D-256 | 2.0 | 110 |
| Melt Flow Rate, g/10 min. 230/2160 | D-1238 | 30 | |
| Specific Gravity | D-792 | 0.910 | |
| Heat Deflection Temperature | | | |
| At 264 psi, F (C) | D-648 | 130 | 54 |
| At 66 psi, F (C) | D-648 | 190 | 88 |
| Linear Mold Shrinkage | D-955 | 0.0140 | |

Values shown are averages and not to be construed as specifications.