



220A Engelwood Drive, Orion, Michigan 48359 USA  
 (Toll Free) 1-877-777-4514 (Intl) 248-845-4515 (Fax) 248-287-4515  
 www.PremierPlasticResins.com info@premierplasticresins.com

---

## *Typical Data Sheet*

---

### PPR-ABS04

#### ABS Low Gloss Natural

Test Description	Method	Properties	
		English	S.I.
Tensile Strength at Yield, psi (Mpa)	D-638	6,000	41.4
Elongation at Break, %	D-638	35	
Flexural Strength, psi (Mpa)	D-790	10,500	72.4
Flexural Modulus (Tangent), psi (Mpa)	D-790	310,000	2,140
Izod Impact (Notched), ft-lb./in (J/m)	D-256	2.7	140
Melt Flow Rate, g/10 min.      230/3800	D-1238	5.0	
Specific Gravity	D-792	1.060	
Heat Deflection Temperature			
At 264 psi, F (C)	D-648	185	85
At 66 psi, F (C)	D-648	195	91
Linear Mold Shrinkage	D-955	0.0060	

---

Values shown are averages and not to be construed as specifications.