



220A Engelwood Drive, Orion, Michigan 48359 USA
(Toll Free) 1-877-777-4514 (Intl) 248-845-4515 (Fax) 248-287-4515
www.PremierPlasticResins.com info@premierplasticresins.com

Typical Data Sheet

PPR-PA602

Nylon 6 13% Glass Fiber Reinforced Heat Stabilized Natural

Test Description	Method	Properties	
		English	S.I.
Tensile Strength at Yield, psi (Mpa)	D-638	15,500	107
Elongation at Break, %	D-638	3.0	
Flexural Strength, psi (Mpa)	D-790	24,300	168
Flexural Modulus (Tangent), psi (Mpa)	D-790	750,000	5,170
Izod Impact (Notched), ft-lb./in (J/m)	D-256	1.0	53
Specific Gravity	D-792	1.220	
Heat Deflection Temperature			
At 264 psi, F (C)	D-648	380	193
At 66 psi, F (C)	D-648	415	213
Linear Mold Shrinkage	D-955	0.0060	

Values shown are averages and not to be construed as specifications.