



220A Engelwood Drive, Orion, Michigan 48359 USA  
 (Toll Free) 1-877-777-4514 (Intl) 248-845-4515 (Fax) 248-287-4515  
 www.PremierPlasticResins.com info@premierplasticresins.com

---

## **Typical Data Sheet**

---

### **PPR-ABSPC02**

#### **ABS/Polycarbonate Alloy Black**

Test Description	Method	Properties	
		English	S.I.
Tensile Strength at Yield, psi (Mpa)	D-638	7,600	52.4
Elongation at Break, %	D-638	100	
Flexural Strength, psi (Mpa)	D-790	12,000	82.8
Flexural Modulus (Tangent), psi (Mpa)	D-790	350,000	2,410
Izod Impact (Notched), ft-lb./in (J/m)	D-256	10	530
Melt Flow Rate, g/10 min.      230/3800	D-1238	3.0	
Specific Gravity	D-792	1.130	
Heat Deflection Temperature			
At 264 psi, F (C)	D-648	225	107
Linear Mold Shrinkage	D-955	0.0060	

---

Values shown are averages and not to be construed as specifications.