



3759 S Baldwin Rd #150, Orion, MI 48359 USA  
 (Toll Free) 1-877-777-4514 (Intl) 248-845-4515 (Fax) 248-287-4515  
 www.PremierPlasticResins.com info@premierplasticresins.com

## *Typical Data Sheet*

### PPR-PPCO10

#### Polypropylene Copolymer 30 Melt 2 Izod Natural

Test Description	Method	Properties	
		English	S.I.
Tensile Strength at Yield, psi (Mpa)	D-638	3,800	26.2
Elongation at Yield, %	D-638		
Flexural Modulus (Tangent), psi (Mpa)	D-790	155,000	1,070
Izod Impact (Notched), ft-lb./in (J/m)	D-256	2.0	110
Melt Flow Rate, g/10 min. 230/2160	D-1238	34	
Specific Gravity	D-792	0.910	
Heat Deflection Temperature			
At 264 psi, F (C)	D-648	133	56
At 66 psi, F (C)	D-648	185	85
Linear Mold Shrinkage	D-955	0.0140	

Values shown are averages and not to be construed as specifications.